

FRACTURED

.150 mil

1" DEEP 5" O.C. RIPPER REBAR

1410

TECHNICAL DATA


Fractured 1410 HIPS High Impact Polystyrene Plastic


Properties	Rating	ASTM
IZOD Impact, ftlbs./in.	-	
@70? F	2.0	D256
@0 <i>?</i> F	1.3	D256
Tensile Strength	3,700 psi	D638
Heat Deflection	188	D695
Vicat Softening	212	D1525
Wt.lb./sq.ft.		
.070 mil	.449	
.090 mil	.577	
.110 mil	.705	
.130 mil	.833	

Fractured 1410 ABS

966

Fractured 1410 ABS Acrylonitrile-butadiene styrene			
IZOD Impact, ftlbs./in.			
	5.6	D256	
@0?	1.9	D256	
Tensile Strength, 73%, psi			
Yield	5,300	D638	
Modulus	330,000	D638	
Flexural Strength 73%, psi			
Yield	9,300	D790	
Modulus	325,000	D790	
Heat Deflection			
@264 psi	199	D648	
@66 psi	211	D648	
Hardness (Rockwell R) 73%	105	D785	
Falling Dart Impact, ftlb.			
@73? F	23		
@40? F	14		
Specific Gravity	1.05	D792	
Wt. lb./sq.ft.			
.070 mil	.451		
.090 mil	.580		
.110 mil	.705		
.130 mil	.833		
.150 mil	.961		





Attachment to Formwork

Thermoform Formliners can be used in precast, tilt-up or cast -in-place applications. Single-use HIP is most frequently used for tilt-up applications and can be installed using Tek drywall screws or pneumatic staplers, spacing should be approximately 6" to 12" on center around the perimeter and 18" to 24" through the center. Double Sided Tape, "Formica Top" adhesive, Heavy Duct Tape or Silicone Caulk are all the common ways to attach formliners. Make sure all surfaces are clean, dry and free of dust and debris. Formliner PE & PPE liners are attached from the back with 3/8" bolts when optional T-nuts are installed.

Form Placement

It is important that forms for architectural concrete be aligned and in common planes. A "Stack up" of manufacturing tolerances can result in forms being in different planes, even when properly aligned. This creates a noticeable "step" in the finished surface, particularly with shallow Formliner patterns.

Rustication

Reveals or rustications are recommended at butted joints so it will allow the features of the liner to appear continuous. All butted joints should be taped and/or caulked to reduce grout leakage.

Form Release

Formliners should be sprayed with high end form release agent before each use and within the same day that concrete is placed. Apply with low flow, wide angle, flat spray nozzle and wipe with a cloth to insure a complete even coat to the entire formliner surface.